

Heat Transfer Vinyl Quick Guide

	DETAILS	PRODUCTION / APPLICATION	CARE INSTRUCTIONS
Easyweed Glitter Electric Stretch Glow Stripflock	Adheres to: • 100% cotton • Poly/cotton blends • 100% uncoated polyester • Leather ----- Blade: 45°/60° Composition: PU Microns/Mils: 90/3.5	• Cut in reverse • Weed • Preheat garment for 2-3 seconds ----- Temp: 305° F/150° C Pressure: Medium Time: 10-15 sec. Peel: HOT or COLD For best performance, cover and reheat for 2-3 seconds	• Wait 24 hours before first wash • Machine wash warm with mild detergent • Do not dry clean • Hang item to dry • Do not bleach • Dry at normal setting -----
	Adheres to: • 100% cotton • Poly/cotton blends • 100% uncoated polyester • Leather • Lightly siliconed nylon • Lycra®/spandex • Sublimated polyester ----- Blade: 60° Composition: PU Microns/Mils: 325/12.8	• Cut in reverse • Weed • Preheat garment for 2-3 seconds ----- Temp: 320° F/160° C Pressure: Firm Time: 10-15 sec. Peel: HOT Can be used as a top layer for other materials. Not recommended to be layered on itself	• Wait 24 hours before first wash • Machine wash warm / mild detergent • Do not bleach • Do not dry clean • Dry at normal setting • Turn inside out -----
	Adheres to: • 100% cotton • Poly/cotton blends • 100% uncoated polyester • Leather • Sublimated polyester ----- Blade: 45°/60° Composition: PU Microns/Mils: 90/3.5	• Cut in reverse • Weed • Preheat garment for 2-3 seconds ----- Temp: 305° F/150° C Pressure: Medium Time: 15sec. Peel: HOT or COLD For best performance, cover and reheat for 2-3 seconds	• Wait 24 hours before first wash • Machine wash warm with mild detergent • Do not dry clean • Hang item to dry • Do not bleach • Dry at normal setting -----
	Adheres to: • 100% cotton • Poly/cotton blends • 100% uncoated polyester • Leather • Lycra® / Spandex ----- Blade: 45°/60° Composition: PU Microns/Mils: 90/3.5	• Cut in reverse • Weed • Preheat garment for 2-3 seconds ----- Temp: 305° F/150° C Pressure: Medium-Firm Time: 15sec. Peel: HOT or COLD For best performance, cover and reheat for 2-3 seconds	• Wait 24 hours before first wash • Machine wash warm with mild detergent • Do not dry clean • Hang item to dry • Do not bleach • Dry at normal setting -----
	Adheres to: • 100% cotton • Poly/cotton blends • 100% uncoated polyester • ----- Blade: 45°/60° Composition: PU Microns/Mils: 90/3.5	• Cut in reverse • Weed • Preheat garment for 2-3 seconds ----- Temp: 305° F/150° C Pressure: Medium-Firm Time: 15sec. Peel: HOT or COLD For best performance, cover and reheat for 2-3 seconds	• Wait 24 hours before first wash • Machine wash warm with mild detergent • Do not dry clean • Hang item to dry • Do not bleach • Dry at normal setting -----
	Adheres to: • 100% cotton • Poly/cotton blends • 100% uncoated polyester • Leather • Sublimated polyester ----- Blade: 45°/60° Composition: PVC Microns/Mils: 410/16.1	• Cut in reverse • Weed • Preheat garment for 2-3 seconds ----- Temp: 320° F/160° C Pressure: Medium Time: 15-20 sec. Peel: COLD For best performance, cover and reheat for 2-3 seconds	• Wait 24 hours before first wash • Machine wash warm / mild detergent • Do not bleach • Do not dry clean • Dry at normal setting • Turn inside out -----